



## Raso G

Medium-fine textured skim coat for rough plasters.



### MAIN AREAS OF USE

#### It is particularly suitable to:

Medium-fine smoothing of cement-based plasters.

#### Recommended applications:

Smoothing of all kinds of plasters .

- Suitable substrates (indoors or outdoors):
- Traditional plasters
- Premixed plasters
- Lime or lime/cement-based plasters
- cNatural hydraulic lime-based plasters
- Refurbishing plasters

### CHARACTERISTICS

**Its versatility of application** allows it to be used on all kinds of surfaces

**Its high mechanical strength** makes it ideal even for semi-structural reinforcements

**Its smoothness and consistency** allow for easy and comfortable application

**Its fibre-reinforced, controlled-shrinkage formulation** minimises cracks and fissures

**Its high bonding power** allows for it to adhere to most common building materials

Compliant with Standard **UNI EN 998-1** as a GP mortar.

### HOW TO USE

#### Preparation of the substrate

The substrate must be cured, clean, flat, cohesive and free of any kind of release agent.

It is always advisable to use a primer to even out absorption.

If necessary, prevent capillary/saline rising with **Neutral Antisale** or **licata Injecto Gel**.

- **New substrates:** no precautions other than those indicated.
- **Deteriorated or crumbling substrates:** remove all crumbling, loose or detaching parts and restore the flatness of the substrate using **licata** products.

#### Preparing the mixture

1\_Pour the product into a clean container containing  $\frac{3}{4}$  of the total mixing water

2\_Mix for about 3-4 minutes with a low-speed mixer, adding the rest of the water gradually. The product ready for application should be a thixotropic, smooth and lump-free mixture.

3\_Let it rest for 1-2 minutes, then stir again before use.

**Raso G** must be used as it is, with the sole addition of clean water. Do not split the packages to use them partially and do not use open bags.

#### Application

Apply the product within 24 hours after laying the base plaster (wet-on-wet technique).

1\_Apply the product using a spatula within 60 minutes of mixing, in two coats spaced 2 to 24 hours apart, depending on the weather conditions.

- 2\_Each layer must not be more than 1.5 mm thick, whereas the final thickness must be between 3 and 4 mm.
- 3\_Complete the work using a sponge trowel, spraying the surface with water and/or wetting the tool.

**N.B.** Do not apply on concrete, plastic coatings or old paint, on substrates prepared with mortars containing resins, on existing stabilising primers (intonachino plaster), gypsum-based plasters and poorly absorbent surfaces.

**PRODUCT INFORMATION**

Appearance	Grey or white powder
Particle size	<0,8 mm;
Powder consumption	4 a 5 Kg/m <sup>2</sup> - (1.1-1.2 Kg/m <sup>2</sup> per mm of thickness)
Mixing water	24-26% of the weight of the powder
Workability time at 20 °C	~ 60 minutes
Application thickness per coat	≤1,5 mm
Application temperature	From +5 ° to +35 °C
Storage in unopened original packaging	12 months in a dry place between +5° and +35°C
Packaging	25 Kg

**REQUIRED PERFORMANCE ACCORDING TO UNI EN 998-1**

Characteristic	Test method	Legal requirement	Performance
Dry density in bulk	EN1015-10		1400-1500 Kg/m <sup>3</sup>
Compressive strength	EN1015-11	CSI - CSIV	CSI
Flexural strength	EN1015-11		0,5 MPa
Adhesion	EN1015-12		≥ 0,3 MPa-FP B
Capillary absorption	EN1015-18	W0-W2	W1
Water vapour coefficient (μ)	EN1015-19		≤ 10
Thermal conductivity ( )	EN1745		0,4 W/mK
Euroclass fire resistance	EN13501-1		A1

**WARNINGS**

- Product for professional use.
- For applications other than those indicated on the data sheet, it is best to perform a suitability check beforehand and/or contact Licata Technical Service for further information.
- Before application, always check that the colour, consistency and appearance correspond. Any claims regarding this will not be accepted once the product has been applied.
- Do not apply the product in extreme conditions, such as on frozen substrates or in the presence of fog/excessive humidity. To avoid aesthetic and functional defects, adequate shielding must be provided in case of direct exposure to sunlight.
- Make sure that the ambient, substrate and product temperatures are between +5°C and +35°C during application and drying.
- Take care of the product until it is completely dry and at least for the first 48-72 hours, protecting it from rain, wind, adverse weather conditions and direct sunlight.
- The temperature and humidity levels can accelerate (if high) or slow down (if too low) the curing process, even drastically, and they can even stop it altogether.
- The presence of scaffolding, the use of natural raw materials and the impossibility of controlling the atmospheric and substrate conditions can lead to signs of shrinkage and unevenness for which Licata SpA shall not be held responsible.
- The fresh product can be washed with water.

**SAFETY**

Protect eyes and hands during application.

Read and keep the latest version of the Safety Data Sheet available for information on the correct disposal, storage and handling of the product.

**NOTES**

This data sheet replaces and voids all previous versions.

The instructions and performance information given in this document are based on our current technical-scientific knowledge and must in any case be considered purely indicative and refer to standard laboratory conditions. The purchaser must, therefore, check that the product is suitable for his specific requirements. All of the documents required for the safe use of **licata SpA** products is available in their most recent versions on the company website [www.licataspa.it](http://www.licataspa.it). Moreover, our technical-commercial network guarantees rapid consultancy and is at your disposal for information and explanations. For further information, contact the Licata Technical Service at [servizio-tecnico@licataspa.it](mailto:servizio-tecnico@licataspa.it)

**Data sheet ref.: TDS P10071 - rev.07/21.**